

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.

THIS PAGE BLANK (USPTO)


INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : B29C 67/24, 41/08, 67/22	A1	(11) International Publication Number: WO 93/23237 (43) International Publication Date: 25 November 1993 (25.11.93)
(21) International Application Number: PCT/BE93/00026 (22) International Filing Date: 18 May 1993 (18.05.93) (30) Priority data: 9200455 18 May 1992 (18.05.92) BE (71) Applicant (for all designated States except US): RECTICEL [BE/BE]; De Broquevillelaan 12, B-1150 Sint-Pieters-Woluwe (BE). (72) Inventors; and (75) Inventors/Applicants (for US only) : JOURQUIN, Lucien [BE/BE]; Coopplaan 156/1, B-9230 Wetteren (BE). DEBAES, Bernard [BE/BE]; De Streep 4, B-8340 Sijsele (BE). DU PREZ, Eddie [BE/BE]; Molenberg 28, B-9660 Brakel (BE).		(74) Agents: VOSSWINKEL, P. et al.; Bureau Gevers S.A., Rue de Livourne 7, Bte 1, B-1050 Brussels (BE). (81) Designated States: AT, AU, BB, BG, BR, CA, CH, CZ, DE, DK, ES, FI, GB, HU, JP, KP, KR, KZ, LK, LU, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SK, UA, US, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>

(54) Title: METHOD FOR MANUFACTURING SELF-SUPPORTING SYNTHETIC TRIM PARTS AND THUS MANUFACTURED TRIM PARTS

(57) Abstract

In the method according to the invention, a layer of polyurethane elastomer for obtaining a polyurethane skin (5) is produced, in a first step, against a mould surface (1). In a second step, a reaction mixture for obtaining a polyurethane foam layer (6) is applied against this polyurethane skin (5). In a third step, a suitable polyurethane or polyisocyanurate reaction mixture for obtaining a rigid synthetic carrier (8) is applied against the polyurethane foam layer (6). In this way, a synthetic trim part is obtained which is easier to recycle. This method can moreover also be performed easier.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LI	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TG	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

"Method for manufacturing self-supporting synthetic trim
parts and thus manufactured trim parts"

5 This invention relates to a method for manufacturing self-supporting synthetic trim parts, in particular car interior parts such as dashboards, doorpanels, consoles and glove compartments, having an elastomeric polyurethane skin, a rigid synthetic carrier and a mainly open-cell polyurethane foam layer there-
between.

10 Such a method is for example already disclosed in the Belgian patent application No. 08900228 of the same applicant. In this method, a layer of polyurethane elastomer is first sprayed against an inner surface of a mould. Then, a previously manufactured
15 insert is positioned into this mould and the space between the insert and the elastomeric layer is filled with a polyurethane foam.

A drawback of this known method consists in that the insert, or in other words the rigid carrier,
20 has to be manufactured in advance in a separate mould. This insert must moreover be accurately positioned into the second mould in order that the foam layer would have everywhere the desired thickness. Especially when this foam layer has to be thin, an exact positioning of the
25 insert is important since a small variation of the foam thickness becomes in this event soon perceptible from the outside. In the case of thin foam layers, extending over a large surface, it is further difficult in the known method to spread the reaction mixture for obtain-
30 ing this foam sufficiently homogeneously over this surface.

- 2 -

The invention aims now to obviate these different drawbacks and this by proposing a new method for manufacturing self-supporting synthetic trim parts which permits moreover the trim parts to be recycled in a simpler way after they have been put out of use.

This method is characterized according to the invention by the fact that, in a first step, a polyurethane skin of a polyurethane elastomer and prepared either or not in advance is applied against a mould surface ; in a second step, a reaction mixture for obtaining said polyurethane foam layer is applied by spraying against said polyurethane skin ; and, in a third step, a suitable polyurethane or polyisocyanurate reaction mixture for obtaining said rigid synthetic carrier is applied against the polyurethane foam layer.

A similar method for manufacturing a trim part having an elastomeric skin, a rigid synthetic carrier and a foam layer therebetween is disclosed in JP-A-2047022. In this known method a PVC/ABS skin having an adjoining polyolefin foam layer is positioned into a mould and the rigid carrier, in this case rigid polyurethane, is subsequently, after having closed this mould, applied against the back of the foam layer by a RIM-proces (Reaction Injection Moulding). According to this Japanese patent application, it is however essential for the polyolefin foam layer to be of a closed cell-structure, in contrast therefore to the polyurethane foam layer according to the present invention. Since the material of these closed cell foam layer and also the material of the skin layer are essentially different from the material of the carrier, the trim parts obtained by this known method are hard to recycle.

According to the invention, however, it has now been found that, when the open-cell polyurethane foam layer is applied by spraying against the polyure-

- 3 -

thane skin, it is possible to apply also against this open-cell foam layer a rigid polyurethane carrier by a mould or a spray process. Due to the open-cell structure of the polyurethane foam layer, it is possible to obtain a trim part having an outer surface which, upon touching, gives a feeling which approaches very closely the touch of a natural leather skin, whereas for a closed-cell structure a rather pneumatically resilient effect is obtained upon touching. Moreover, it has been observed that by the spray process a foam layer having a natural skin is obtained which prevents the reaction mixture for the carrier from penetrating therein while a good adhesion is anyway also obtained. The used spray technique for applying the foam layer against the polyurethane skin allows moreover to vary the thickness of this foam layer from place to place as desired.

An important advantage of the method according to the invention is further that trim parts are obtained which are much easier to recycle compared to the existing parts. As a matter of fact, the existing trim parts, in particular the existing dashboards, are composed of different synthetic materials, this a.o. in order to be able to meet the severe quality requirements to which these products are subjected. In order to permit such composite materials to be recycled, a prior separation is required which involves usually important technical problems and which is therefore commercially not feasible.

In a first particular embodiment of the method according to the invention, the reaction mixture for obtaining the synthetic carrier is applied by spraying against the polyurethane foam layer, in particular by means of a two-component spray gun. This method offers the advantage that the foam layer will not be deformed and that the polyurethane skin will consequently maintain its shape after demoulding.

- 4 -

In a further particular embodiment of the method according to the invention, the polyurethane skin and the polyurethane foam layer are applied in a mould and, in said third step, this mould is closed and the reaction mixture for obtaining the synthetic carrier is injected into this mould against the polyurethane foam layer. In this way there is also obtained a dimensionally stable back which does not require any further finishing.

In a preferred embodiment of the method according to the invention, a polyurethane skin is produced, in said first step, having a thickness of 0.3 to 1.3 mm, and preferably a thickness of 0.4 to 1.0 mm. By manufacturing such thin polyurethane skins, it is possible to obtain a trim part, the visible side of which shows a so-called leather touch, especially when the underlying foam layer has a thickness of 1 to 7 mm, and more particularly of 2 to 3 mm.

The invention further relates to self-supporting synthetic trim parts which are obtained by applying the hereabove described method according to the invention and which hence comprise an elastomeric polyurethane skin, a rigid polyurethane or polyisocyanurate carrier and a polyurethane foam layer therebetween.

Further particularities and advantages of the method and the trim parts according to the invention will become apparent from the following description of some particular embodiments of the invention. This description is only given by way of example and is not intended to limit the scope of the invention. The reference numerals used hereinafter relate to the annexed drawings wherein :

Figure 1 shows a schematic representation of the different steps of a first embodiment of the method according to the invention ;

- 5 -

Figures 2, 3 and 4 show schematically the different steps of a second embodiment of the method according to the invention ; and

Figure 5 is analogous to figure 4 but
5 relates to a different last step.

In these different figures, the same reference numerals relate to the same or to analogous elements.

The invention generally relates to a
10 method for manufacturing self-supporting synthetic trim parts having an elastomeric polyurethane skin, a rigid synthetic carrier and a polyurethane foam layer there-between. Such trim parts are especially used as car interior parts such as dashboards, doorpanels, consoles,
15 glove compartments, etc...

In a specific embodiment of the method according to the invention; the different layers of the trim parts are mainly made of polyurethane so that a complex is obtained which is easier to recycle. The
20 presently existing trim parts on the contrary consist of complexes of different materials such as PVC, ABS, PU, etc., which, in view of their difference in nature and composition, cannot or are hardly to be recycled simultaneously. These known trim parts require therefore a
25 previous separation of the composing components which cannot or which is difficult to realize.

The invention provides now a new method which permits trim parts, as described hereinabove, to be manufactured in a technically and economically well
30 considered way substantially exclusively on the basis of polyurethane. To this end, a layer of polyurethane elastomer for obtaining the polyurethane skin is produced, in a first step, against a mould surface. Then, a reaction mixture for obtaining the mainly open-cell
35 polyurethane foam layer is applied, in a second step, by spraying against the polyurethane skin. Finally, a

- 6 -

suitable polyurethane or possibly polyisocyanurate reaction mixture for obtaining the rigid synthetic carrier is applied, in a third step, against the polyurethane foam layer.

5 Figure 1 shows schematically a first embodiment of the method according to the invention.

On the mould surface 1 of a first part 2 of a two-part mould 2,3 there is applied, by spraying by means of a spray gun 4, a polyurethane elastomer layer
10 5 which forms the skin 5 of the trim part. This can be done according to the technique described in the Belgian patent application No. 8700792 of the same applicant.

In a second step, a reaction mixture for obtaining a polyurethane foam layer 6 is sprayed by
15 means of a second spray gun 7 against the back of the polyurethane skin 5, preferably when the skin 5 is still somewhat sticky.

Then, in a third step, the mould 2, 3 is closed and a suitable reaction mixture for obtaining the
20 rigid polyurethane carrier 8 is injected into the mould cavity by means of a third spray gun 9.

For producing the polyurethane skin 5 a light-stable, mass-stained colored polyurethane reaction mixture is sprayed in the first embodiment, as shown in
25 figure 1, against the mould surface 1. Such reaction mixtures are for example disclosed in the Belgian patent application No. 8900067 of the same application. These light-stable reaction mixtures are based on an aliphatic polyisocyanate.

30 In a variant embodiment, a light-stable colored polyurethane paint or in o.w. a so-called PU in mold paint, is applied first, in the first step, onto the mould surface. This paint composes together with the elastomeric layer applied thereto subsequently, the
35 polyurethane skin 5. In this embodiment, use can be

- 7 -

made of an aromatic polyurethane system for the elastomeric layer.

5 In a further variant embodiment, the polyurethane skin is made of thermoplastic polyurethane (TPU). This TPU can be prepared on the basis of aromatic, aliphatic or alicyclic isocyanates. Use can be made of a TPU foil which is applied first by thermoforming against a mould surface. This thermoforming process can be performed in the mould 2, 3 or possibly in
10 another mould after which the thermoformed TPU foil is positioned then into the mould 2, 3. In order to make this foil to fit well against the mould surface 1, this foil is preferably sucked against this surface. The TPU skin can also be prepared on the basis of a TPU powder,
15 in particular by a so-called powder slush molding process in a heated rotating mould. The obtained TPU skin can subsequently also be placed against the mould surface 1 of the mould 2, 3.

20 The polyurethane skins are usually manufactured against a mould surface, the surface structure of which is provided for giving the skins the look of natural leather. The open-cell polyurethane foam 6 which is applied against the back of these skins 5, provides for a so-called soft touch. The reaction
25 mixture for obtaining the polyurethane foam layer 6 is preferably composed in such a manner that a semi-flexible polyurethane foam is obtained. Especially the amount of so-called cross-linkers in the reaction mixture is important in this respect. In a particular
30 embodiment, use is made in this reaction mixture substantially exclusively of water as blowing agent. The polyisocyanate component is for example based on MDI.

35 In a preferred embodiment, an open-cell polyurethane foam layer 6 having a thickness of 1 to 7 mm and preferably of 2 to 3 mm is applied. In order to approach as much as possible the touch of natural

- 8 -

leather, such a foam layer 6 is combined with a polyurethane skin 5 having a thickness of 0.3 to 1.3 mm and preferably of 0.4 to 1.0 mm. Since such thin skins are hard to transfer from one mould to another, they are preferably produced directly in the mould 2, 3 by a spray process.

In order to finish the trim part further on the back or inner side, a polyurethane finishing layer may also be applied against the mould surface 10 of the second mould part 3 in the first step.

In a first embodiment, a previously produced TPU skin is applied to this end for example against this mould surface 10.

In a further embodiment, a polyurethane paint is sprayed against the mould surface 10, either or not followed by the application of an elastomeric polyurethane layer and a further polyurethane foam layer. In the latter case, a leather like coating is also obtained on the back.

Instead of the combination of the polyurethane paint layer and the elastomeric layer, it is of course also possible to use a light-stable elastomeric polyurethane layer.

The rigid carrier 8 can, as shown in figure 1, be produced in a mould cavity by injecting a suitable reaction mixture. This offers the advantage that also the back of the trim part has the right dimensions and is as such ready for mounting. The reaction mixture for obtaining the rigid carrier 8 may further also be applied by spraying against the back of the complex of elastomeric skin 5 and foam layer 6. In this way substantially no pressure is exerted onto the foam layer 6 and deformations of this foam layer 6 are consequently avoided. Avoiding such deformations and especially local deformations, for example against corners of the mould surface, is important. Indeed,

- 9 -

after demoulding, the compressed foam layer will re-expand and external deformations of the skin of the trim part will occur on places where the foam layer expands stronger, or in o.w. on places where the foam layer was stronger compressed. The rigid carrier can be produced by rigid PU-systems, in particular by the so-called SRIM systems.

In case the rigid carrier 8 is produced in a mould cavity, the reaction mixture for obtaining this carrier is preferably composed and applied in such a manner in the mould cavity that during applying and curing of this reaction mixture a pressure is exerted onto the polyurethane foam layer 6 which is lower than the pressure required for a 25% compression of this polyurethane foam layer and which is preferably lower than the pressure required for a 10% compression of the foam layer. This compressions have to be measured on a place where the foam layer rests against a flat surface. In order to reduce the compression of the foam layer 6 when applying the reaction mixture for obtaining the rigid carrier as much as possible, use is made of a reaction mixture which has a viscosity lower than 3000 mPa.s at 25°C and preferably lower than 1000 mPa.s. The components of this reaction mixture are preferably brought to a temperature of 20 to 100°C and in particular to a temperature comprised between 45 and 70°C. As result of the viscosity reduction, a lower pressure is required for injecting the reaction mixture.

In a particular embodiment, the reaction mixture for obtaining the carrier is substantially free of blowing agents so that substantially no pressure is generated during the reaction of the different components. This reaction mixture comprises typically a polyol and a polyisocyanate component. The polyol component comprises up to 1 % by weight at the most and preferably up to 0.1 % by weight at the most of water.

- 10 -

In a further particular embodiment, the reaction mixture for obtaining the carrier does comprise blowing agents so that the carrier is composed of a rigid polyurethane foam. When use is made in this case of a closed mould, an accurate control of the total amount of injected reaction mixture and of the amount of blowing agent is required to avoid an excessive compression of the foam layer.

In a preferred embodiment, the carrier is reinforced by means of glass fibres so that the shrinkage of the carrier is under control and the rigidity is increased. The glass fibres may be admixed to the reaction mixture for obtaining the rigid carrier, for example in a so-called SRIM system. Further use can be made of a glass fibre mat which is placed over the foam layer before applying the reaction mixture for obtaining the rigid carrier. The glass fibre mat is preferably applied when the foam layer is still sticky. The glass fibre mat and the glass fibres admixed into the reaction mixture may possibly be used in combination.

In order to illustrate the method according to the invention, four concrete examples are further given hereinafter of the method according to the invention and especially of the chemical formulations of the polyurethane skin, the foam layer as well as of the rigid carrier.

Example 1

The method according to this example is in particular suited for manufacturing a glove compartment cover having a surface of for example 600 cm². The model of this glove compartment cover includes no undercuts so that only one two-part mould, analogous to the one indicated in figure 1, has to be used for the whole process. The lowermost part 2 of this mould 2,3 comprises a galvanoplate showing a leather structure.

- 11 -

In a preparatory step, the lowermost 2 and the uppermost mould halve 3 are treated with a mould release agent such as for example Acmosil 180 SFC (Acmos) or Aquathan 61-360 (Block Chemie).

5 On the lowermost mould part 2 a polyurethane skin 5 is produced by means of a two-component spray gun 4. For manufacturing this skin 5 use is made of the Colofast[®] Spray BLS system (trademark of Recticel) which allows to produce a mass-stained
10 light-stable microcellular elastomeric skin. The first component of this system, i.e. Isofast 3430 A (Recticel), is supplied at a flow rate of 3.67 g/sec, whereas the second component, i.e. Polyfast 3530 A (Recticel), is supplied at a flow rate of 6.33 g/sec.
15 The total flow rate comprises therefore 10.0 g/sec. The controlled spray time comprises 6 sec. In this way a polyurethane skin 5 is obtained having a thickness of about 1 mm.

Immediately after the reaction, a layer of
20 about 2 mm semi-flexible open-cell polyurethane foam 6 is applied on top of this polyurethane skin 5 by means of a second two-component spray gun 7. For producing this foam layer 6 use is made of the following water-blown MDI system :

25 Polyol component :

Speciflex NM 805 (Dow)	100	}	104.95
Butanediol 1,4 (Hüls)	3		
30 Water	0.9		
Dabco 33Lv (Air Products)	1.0		
Fomrez UL28 (Witco)	0.05		

35 Isocyanate component : Suprasec VM12 (I.C.I.) 24.12
Isocyanate index : 60
Flow rate of polyol component : 4.88 g/sec
Flow rate of isocyanate component : 1.12 g/sec

- 12 -

Total flow rate : 6.00 g/sec.

After a controlled spray time of 6 sec. with the spray gun 7, a thin layer of semi-flexible open-cell foam provided with a natural skin towards the side of the gun is obtained having a total thickness of ± 2 mm and the so-called overall density of which comprises ± 450 gr/litre.

By adjusting the robot program the thickness of the semi-flexible layer may vary from place to place. This thin foam layer gives the elastomeric "Colofast" skin, a so-called soft touch specific to natural leather.

Before closing the mould for the third operation, the production of the rigid carrier, a glass mat is applied onto the surface of the freshly sprayed semi-flexible foam which is still sticky, for example of Unifill U816 : 450 gr/m² type. The mould is closed and the formed cavity is filled with the two-component rigid PU system 8 consisting of :

20	Polyol PU 1397 (Bayer)	9.00 gr/sec.
	Iso PU 1511 (Bayer)	9.00 gr/sec.
	Total	18.00 gr/sec.
	Injection time	5 sec.
	Polyol component :	
25	Temperature	45°C
	Viscosity (at 45°C)	340 mPa.s
	Water content	0.06
	Isocyanate component :	
	Temperature	45°C
30	Viscosity (at 45°C)	65 mPa.s

In this way a rigid carrier of a thickness of ± 3 mm which forms a monolith unit with the semi-flexible foam layer and the skin is produced.

After demoulding, a dimensionally stable glove compartment cover is obtained since the pressure exerted by the rigid PU system was lower than the

- 13 -

compression force of the semi-rigid foam layer at a deformation of 0.2 mm. The pressure required for a 10% deformation (± 0.2 mm) of the semi-flexible foam is 13 KPa at 80°C.

5

Example 2

This example is identical to Example 1 except for the fact that the "Colofast" polyurethane skin is replaced by a so-called polyurethane inmold paint followed by a two-component aromatic microcellular elastomeric system.

10

The inmold paint is in this case a light-stable two-component PU system, in particular Isothan-IMP-2K-Klarlack ME 170 of ISL Chemie.

Some inmold paints such as for example Rimbond 200 of Mc. Pherson Industrial Coatings have self release properties, so that the amount of a mould release agent on the lowermost mould part 2 can be reduced or avoided. The thickness of the inmold paint film comprises $\pm 20 \mu$.

20

After evaporation of the solvent, which takes about 30 sec., the second layer, a PU elastomer, is applied by means of a two-component gun. This solventless elastomeric system consists of :

1. Polyol-component

25 Polyethertriol : condensate of propylene en ethylene oxyde on glycerine - IOH index 28 - content of primary OH groeps 85 % 90

Dabco 33 Lv (Air Products) 2.25

Butanediol (Hüls) 7.9

30 Color paste 5
105.15

Viscosity at 25°C in mPa.s 1060

Viscosity at 45°C in mPa.s 320

2. ISO-component

35 Isocyanate RMA 200 (Dow) 43.5

Viscosity at 25°C in mPa.s 620

- 14 -

Viscosity at 45°C in mPa.s 126

This system is based on aromatic isocyanates and is therefore not light-stable or colored. These lacking properties are obtained by the previously applied PU inmold paint. In this way, there is also obtained a light-stable colored 100% PU skin.

Example 3

In this example an instrument panel is manufactured by means of a mould showing undercuts (see figures 2, 3 and 4).

As shown in figure 2, a microcellular mass-stained light-stable "Colofast" spray skin 5, as in example 1, is prepared by means of a two-component spray gun 4 in a separate galvano plate 11 provided with a mould release agent.

Immediately after this operation, a layer of ± 3 mm of the same waterblown MDI semi-flexible foam 6 as in example 1 is applied, in the same open mould by means of a two-component gun 7 on top of the skin 5 (see figure 3). As indicated in figure 3, the undercuts 14 in the mould are also filled with the semi-flexible foam and this in order to permit the rigid core to be demoulded later. After the demoulding, this flexible complex is transferred to a second mould 2, 3 provided with the necessary slides 12 (see figure 4). After positioning the skin - foam complex, the uppermost mould part 3 is closed. The so-formed cavity 13 is filled with a low viscosity two-component rigid PU system which consists in particular of :

Polyol Daltocast 4 (ICI)	100 parts
ISO Suprasec DNC (ICI)	136 parts
Polyol temperature 95°C	Viscosity 20 mPa.s
Isocyanate temperature 45°C	Viscosity 65 mPa.s
Water content of the polyol 0.05 %	

This cavity 13 can be filled either or not before closing the upper part 3 with a glass fibre mat.

- 15 -

After 5 min., the complex is demoulded and an instrument panel is obtained consisting of a rigid PU carrier, a light-stable skin and a soft touch layer therebetween.

5

Example 4

This example differs from example 3 in that the non-blown rigid polyurethane system for obtaining the carrier is replaced by a blown rigid foam system of a lower density and a good flow ; in particular the Baydur STR/F/system reinforced with glass fibres. The used PU system consists of :

Polyol PU 0768C (Bayer)	100 parts
Isocyanate 44 V10 F (Bayer)	170 parts

After a substantially free rise of this PU system in the mould cavity 13, a rigid foam having a specific weight (RG) of about 60 kg/m³ is obtained. In order to obtain a sufficient rigidity in case of this lighter rigid foam system, the mould cavity has to be thicker than in example 3, as shown in figure 5.

20

Example 5

This example relates to a method which is in particular suited for manufacturing a doorpanel, only one side of which is provided with a decorative polyurethane skin. This method allows to produce in one one-part mould, without undercuts, a self-supporting doorpanel provided with a soft touch layer 6 between the decorative polyurethane skin 5 and the rigid polyurethane carrier 8.

To this end, use can be made for example of a mould which is analogous to the lowermost mould half 2 of the mould 2, 3 shown in figure 1. In this embodiment, the mould is therefore restricted to an open galvano-plate which represents the visible side of the doorpanel.

35

On this galvanoplate, the polyurethane skin 5 and the foam layer 6 are applied successively by

- 16 -

means of the spray guns 4 and 7 in the same way as in example 1. Immediately afterwards, instead of using a pouring system for making the rigid polyurethane carrier, this carrier is applied according to a two-component spray system.

In particular use is for example made of the following "Elastocoat" system of Elastogran :

Polyol component Elastocoat C 6815/65 100 parts

Isocyanate component Elastocoat C 6815/65 71 parts

10 Viscosity at 25°C : polyol component 1650 \pm 100 mPa.s
isocyanate comp. 600 \pm 50 mPa.s

Both components are used at a temperature of 45 to 60°C.

The reaction time comprises at this temperature 3 \pm 2 sec. In view of the high reactivity, a high pressure

15 spray gun has to be used. The total flow rate comprises \pm 30 gr/sec. so that for a surface of 2000 cm² and a layer thickness of \pm 3 mm, a spray time of \pm 20 sec. is required. The so-obtained rigid PU carrier has a bending module of \pm 600 N/mm² according to DIN 58457.

20 Since no blowing agents are incorporated into this system, a quasi non-cellular material having a density of between 0.95 and 1.05 gr/cm³ is obtained. The bending module can be increased by making use of a glass fibre reinforcement.

25 In a variant of this method, the quasi non-cellular rigid PU carrier can be replaced by an expanded PU rigid foam spray system which is known per se as insulating material. In view of the lower density of such a foam (\pm 40 gr/dm³) the PU rigid foam carrier
30 will occupy in this case a larger volume (thickness) for a same rigidity.

It is clear that the invention is in no way limited to the hereabove described embodiments and that many modifications can be considered within the
35 scope of this invention a.o. as to the kind of the skin, the foam layer and the rigid carrier as well as the

- 17 -

techniques for applying the skin and the foam layer and for injecting the rigid carrier.

- 18 -

CLAIMS

1. A method for manufacturing self-supporting synthetic trim parts, in particular car interior parts such as dashboards, doorpanels, consoles and glove compartments, having an elastomeric polyurethane skin (5), a rigid synthetic carrier (8) and a mainly open-cell polyurethane foam layer (6) therebetween, characterized in that, in a first step, a polyurethane skin (5) of a polyurethane elastomer and prepared either or not in advance is applied against a mould surface (1) ; in a second step, a reaction mixture for obtaining said polyurethane foam layer (6) is applied by spraying against said polyurethane skin (5) ; and, in a third step, a suitable polyurethane or polyisocyanurate reaction mixture for obtaining said rigid synthetic carrier (8) is applied against the polyurethane foam layer (6).

2. A method according to claim 1, characterized in that the reaction mixture for obtaining the synthetic carrier (8) is applied by spraying against the polyurethane foam layer (6), in particular by means of a two-component spray gun.

3. A method according to claim 1, characterized in that the polyurethane skin (5) and the polyurethane foam layer (6) are applied in a mould (2, 3) and, in said third step, this mould is closed in the reaction mixture for obtaining the synthetic carrier (8) is injected into this mould against the polyurethane foam layer (6).

4. A method according to claim 3, characterized in that the reaction mixture for obtaining the synthetic carrier (8) is composed and applied in such a manner into the mould (2,3) that, during applying and curing of this reaction mixture, a pressure is exerted onto the polyurethane foam layer (6) which is lower than the pressure required for a 25 % compression of this

- 19 -

polyurethane foam layer and which is preferably lower than the pressure required for a 10 % compression of the polyurethane foam layer.

5 5. A method according to claim 3 or 4, characterized in that the reaction mixture for obtaining the synthetic carrier (8) has a viscosity at 25°C lower than 3000 mPa.s and preferably lower than 1000 mPa.s when applying it into the mould.

10 6. A method according to any one of the claims 3 to 5, characterized in that the reaction mixture for obtaining the synthetic carrier (8) comprises a polyol component and a polyisocyanate component and is substantially free of blowing agents, the polyol component comprising upto 1 % by weight at the most and
15 preferably upto 0.1 % by weight at the most of water.

 7. A method according to any one of the claims 3 to 6, characterized in that use is made of a mould (2,3) comprising in its closed position at least two opposing mould surfaces (1, 10), against both of
20 which there is applied a polyurethane skin (5) and a polyurethane foam layer (6) and between both foam layers the reaction mixture for obtaining the synthetic carrier (8).

 8. A method according to any one of the
25 claims 1 to 7, characterized in that the carrier (8) is reinforced by means of glass fibres.

 9. A method according to claim 8, characterized in that a glass fibre mat is applied over the polyurethane foam layer (6) before applying the reaction
30 mixture for obtaining the synthetic carrier (8).

 10. A method according to claim 8 or 9, characterized in that glass fibres are admixed in the reaction mixture for obtaining the synthetic carrier (8).

- 20 -

11. A method according to any one of the claims 1 to 10, characterized in that the polyurethane skin (5) is made of a thermoplastic polyurethane (TPU).

5 12. A method according to any one of the claims 1 to 10, characterized in that, in a first step, in order to produce said polyurethane skin (5), a light-stable mass-stained polyurethane reaction mixture is sprayed against said mould surface (1).

10 13. A method according to any one of the claims 1 to 10, characterized in that, in a first step, in order to produce said polyurethane skin (5), a light-stable coloured polyurethane paint, i.e. a so-called "PU inmold paint" is applied onto the mould surface (1) and a polyurethane reaction mixture is subsequently sprayed
15 against this paint.

14. A method according to any one of the claims 1 to 13, characterized in that, in said first step, a polyurethane skin (5) is produced having a thickness of 0.3 to 1.3 mm, and preferably a thickness
20 of 0.4 to 1.0 mm.

15 15. A method according to any one of the claims 1 to 14, characterized in that, in said second step, a polyurethane foam layer (6) is produced having a thickness of 1 to 7 mm, and preferably a thickness of
25 2 to 3 mm.

16. A method according to any one of the claims 1 to 15, characterized in that the reaction mixture for obtaining the polyurethane foam layer (6) is composed so as to obtain a semi-flexible foam layer.


30 17. A method according to claim 16, characterized in that use is made as blowing agent in the reaction mixture for obtaining the polyurethane foam layer (6) substantially exclusively of water.

35 18. A self-supporting synthetic trim part, in particular obtained by applying a method according to any one of the claims 1 to 17, character-

- 21 -

ized in that it comprises an elastomeric polyurethane skin (5), a rigid polyurethane or polyisocyanurate carrier (8) and a polyurethane foam layer (6) therebetween.

5



2/5




Fig. 2.

3/5






Fig. 3.

4/5



F i g . 4 .

5/5



F i g . 5 .

I. CLASSIFICATION OF SUBJECT MATTER (If several classification symbols apply, indicate all) ⁶		
According to International Patent Classification (IPC) or to both National Classification and IPC		
Int.Cl. 5 B29C67/24; B29C41/08; B29C67/22		
II. FIELDS SEARCHED		
Minimum Documentation Searched ⁷		
Classification System	Classification Symbols	
Int.Cl. 5	B29C	
Documentation Searched other than Minimum Documentation to the extent that such Documents are included in the Fields Searched ⁸		
III. DOCUMENTS CONSIDERED TO BE RELEVANT⁹		
Category ¹⁰	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³
X	WORLD PATENTS INDEX LATEST Derwent Publications Ltd AN90-095310; DW9013 & JP-A-2047022 (NIPPPON PLAST) 16 Feb 1990	1, 18
Y	DE,A,3 043 044 (METZLER SCHAUM) 3 June 1982 see page 5, line 12 - line 21 see page 6, line 17 - line 23	1,8-15, 17, 18
Y	EP,A,0 386 818 (RECTICEL) 12 September 1990 cited in the application see the whole document	1,8-15, 17, 18
A	WO,A,8 500 755 (TAA) 28 February 1985 see claims 1,5-8,14,16-25	1,2, 6-11,14, 18
-/-		
<p>¹⁰ Special categories of cited documents:</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"Δ" document member of the same patent family</p>		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search		Date of Mailing of this International Search Report
19 JULY 1993		04. 08. 93
International Searching Authority		Signature of Authorized Officer
EUROPEAN PATENT OFFICE		PHILPOTT G.R.

III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)

Category °	Citation of Document, with indication, where appropriate, of the relevant passages	Relevant to Claim No.
A	EP,A,0 332 495 (HUTCHINSON) 13 September 1989 see the whole document ----	1,3,8, 10,18
A	DE,A,2 915 474 (H G. RING) 13 November 1980 see page 8, line 5 - line 31 see page 9, line 18 - line 22 ----	1,3,16, 18
A	DE,A,2 157 921 (J RUHNAU) 30 May 1973 see the whole document -----	1,2,8, 10,11, 16,18

**ANNEX TO THE INTERNATIONAL SEARCH REPORT
ON INTERNATIONAL PATENT APPLICATION NO.**

**BE 9300026
SA 73507**

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information. **19/07/93**

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE-A-3043044	03-06-82	None	
EP-A-0386818	12-09-90	BE-A- 1002899 AU-B- 624478 AU-A- 5012690 CA-A- 2011375 JP-A- 3027914 US-A- 5116557	16-07-91 11-06-92 06-09-90 03-09-90 06-02-91 26-05-92
WO-A-8500755	28-02-85	DE-A- 3329230 CA-A- 1252341 DE-A- 3468983 EP-A, B 0152440 JP-T- 60501991 US-A- 4806302 US-A- 4713032	28-02-85 11-04-89 03-03-88 27-01-88 21-11-85 21-02-89 15-12-87
EP-A-0332495	13-09-89	FR-A- 2628027 JP-A- 1272426	08-09-89 31-10-89
DE-A-2915474	13-11-80	None	
DE-A-2157921	30-05-73	None	

EPO FORM PCT/93

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

THIS PAGE BLANK (USPTO)